



مختبرات ويمبي لش.ذ.م.م.  
WIMPEY LABORATORIES L.L.C.

**TEST REPORT ON COMPRESSIVE STRENGTH**

Client	Sabin Plastic Industries L.L.C. Sharjah, UAE.		
Contractor	N.G	Lab Report No.	WD-R-230109-0394
Consultant	N.G	Sample No.	WD-S-230109-0415
Production Batch Quantity	N.G	Request No.	WD-Q-230109-0086
Sample Description	75/50mm Chair Spacer	Date Received	09/01/2023
Client reference/PO	N.G	Date Tested	13/01/2023
Test Method	IHP in accordance with ASTM D1621-16	Date Reported	13/01/2023
Specimen Height	33.09 mm	Conditioning Procedure	24 hours at 45°C
Sample brought in by	Client	Test Temperature	23°C & 50% humidity
No of sample tested	1 No.	Tested By	RB
Wimpey Lab	223010916		

**Test Results**

Specimen Number	Length (mm)	Width (mm)	Force (N)
1	98.90	33.09	1077

**Legends: N.G – Information Not Given**

Remarks: Photos attached in Annex A

Signed for and on behalf of Wimpey Laboratories L.L.C.

S.Sarath Kumar  
Head of Department

Test results relate only to the samples tested.

This report shall not be reproduced except in full, without the written approval of the laboratory.

-End of text-





مختبرات ويمبي ش.ذ.م.م.  
WIMPEY LABORATORIES L.L.C.

Report Number: WD-R-230109-0394  
Sample Number: WD-S-230109-0415

**ANNEX -A**  
**SAMPLE PHOTOS**



Before Test




After Test





مختبرات ويمبي ش.ذ.م.م.  
WIMPEY LABORATORIES L.L.C.

Report Number: WD-R-230109-0394  
Sample Number: WD-S-230109-0415



### TEST GRAPH

